

SCR ALLIANCE

DESCRIPTION AND SCOPE OF APPLICATION

An elastomeric membrane modified SBS with polyester reinforcement manufactured in 1 m wide and 20 m long rolls.

USE

SCR ALLIANCE (Resilient under layer) is a mechanically fixed membrane on wooden, metallic or concrete deck by means of screws and washers, the ideal solution for reroofing.

The underside without bitumen coating prevents adherence and allows semi-independence.

The spot fixings and strong non woven polyester carrier offer a high strength to pull out, puncturing and cracking.

COMPOSITION

Main surface	Torch on film
Longitudinal overlap surface	Sanded
Longitudinal overlap under face	Sanded
Blend	Fillerized SBS (Styrene-Butadiene-Styrene) elastomeric bitumen
Reinforcement	Non woven polyester
Underface	Non woven polyester


DIMENSIONAL CHARACTERISTICS

Nominal thickness on the longitudinal selvedge (mm)	2
Nominal thickness on the main surface (mm)	2
Longitudinal selvedge nominal width (mm)	50
Roll nominal length and width (m)	20 x 1

PERFORMANCES

KIND OF TEST	Reference Norm	Units	Average values
Tensile strength at max	EN 12 311-1: 1999	N/50mm	650 x 350
Elongation at max	EN 12 311-1: 1999	%	35 x 35
Nail tearing resistance	EN 12 310-1	N	200 x 200
Cold temperature flexibility	EN 1109	°C	≤ - 20
Heat flow test	EN 1110	°C	≥ 100
Dimensional stability	EN 1107-1	%	≤ - 0.5
FIT classification	See the relevant technical agreement		

ISO 9001 REFERENCE DOCUMENT

. Our company has been awarded the ISO 9001 certificate for all its establishments in France.	
. The Technical Agreement SCR ALLIANCE is the ISO 9001 reference document.	

Product Technical Information

ITA/ATEXP/050

Rev.10 - 27/07/07

Page 2/2

PACKAGING

Rolls quantity per truck pallet	20
Rolls quantity per container pallet	20
Rolls quantity per wooden box	20
Nominal weight / m ² (kg/m ²)	1.85
Nominal weight / roll (kg)	37

GENERALITIES ABOUT APPLICATION

Using	The generalities about the product using are set out in the ZSA STANDARD
Application	The generalities about the product application are set out in the ZTA STANDARD
Overlaps	Current building practices concerning overlaps are set out in the ZRA STANDARD
Slopes	Current building practices concerning slopes are set out in the ZPA STANDARD

COMPLEMENTARY INFORMATIONS

Product identification	
Values	Where 2 values for given characteristics are shown, the first is for longitudinal direction and the second is for the cross direction.
Tolerances	The average values derived from standard tests and are subject to the usual production variations. The indicated average values comply with the UEAtc standard and project prEN 13707. The nominal value tolerances comply with the UEAtc standards. Some slight variations can be noticed as the values are based on the average values obtained from several plants.
Modification(s)	Our company reserves the right to modify its composition as a result of technologic and experiments improvements. This product data sheet supersedes the previous edition, to obtain the up-date technical data sheet, please contact our technical department.
Hazardous classification	It is not classified as dangerous according to the international regulation (ADR, RID, IATA, et RTMDR)
Complementary information	This product is only a product technical data sheet, regarding each waterproofing design, please, consult the concerned technical agreement and in case of doubt contact our technical department.
Storage	This product is packaged in rolls set up vertically on pallet or wooden box. It must be stored vertically under shelter, away from heat sources.