

ADESULO G

DESCRIPTION AND SCOPE OF APPLICATION

High performance reinforced SBS elastomeric bitumen membrane semi-adhered and self-finished by coloured ceramic mineral granules or slates, for waterproofing works. It features factory applied self adhesive strips for partial bonding and the PROFIL SYSTEM (SIPLAST patent), which by selvedge scarifying, highly improves the installation efficiency (homogenous film burn out, total).

. This product is for use as membrane of a single layer self protected waterproofing system for inaccessible roof ; or as a roofing membrane for upstand , gutters, penetrations and others roof details. It can be also used for miscellaneous works. In either case, this product must be used in accordance with the relevant technical specifications.

COMPOSITION

Main surface	Coloured granules. (colour : contact our company)
Longitudinal overlap surface	Scarified thermo-fusible film
Blend	Fillerized SBS (Styrene-Butadiene-Styrene) elastomeric bitumen
Reinforcement	Non woven PY stabilized impregnated with fillerized SBS (Styrene-Butadiene-Styrene) elastomeric bitumen
Underface	Siliconised release at self adhesive blend

DIMENSIONAL CHARACTERISTICS

COLOURS	Slate grey 30 and Schist light 1	Others colours
Nominal thickness on the longitudinal selvedge (mm)	4	4
Nominal thickness on the main surface (for information only) (mm)	4,8	5
Longitudinal selvedge nominal width (mm)	120	120
Roll nominal length and width (m)	7x 1	7 x 1

PERFORMANCES

KIND OF TEST	Reference Norm	Units	Average values
Tensile strength at max	EN 12 311-1: 1999	N/50mm	700 x 600
Elongation at max	EN 12 311-1: 1999	%	45 x 45
Nail tearing resistance	EN 12 310-1	N	300 x 300
Cold temperature flexibility	EN 1109	°C	≤ - 20
Heat flow test	EN 1110	°C	≥ 100
Dimensional stability	EN 1107-1	%	≤ - 0,3
Static puncture resistance	EN 12730	kg	15
Dynamic puncture resistance	EN 12691	mm	10
Fit classification	Not tested		

ISO 9001 REFERENCE DOCUMENT

. Our company has been awarded the ISO 9001 certificate for all its establishments in France.

. The French product technical data sheet is the ISO 9001 reference document.



Siplast SA certified ISO 9001

PACKAGING

COLOURS	Slate grey 30 and Schist light 1	Others colours
Rolls quantity per truck pallet	20	20
Rolls quantity per container pallet	25	25
Rolls quantity per wooden box	20	20
Nominal weight / m ² (kg/m ²)	6.2	6.5
Nominal weight / roll (kg)	43.4	45.7

GENERALITIES ABOUT APPLICATION

Using	The generalities about the product using are set out in the ZSA STANDARD
Application	The generalities about the product application are set out in the ZTA STANDARD
Overlaps	Current building practices concerning overlaps are set out in the ZRA STANDARD
Slopes	Current building practices concerning slopes are set out in the ZPA STANDARD

COMPLEMENTARY INFORMATIONS

Product identification	
Values	Where 2 values for given characteristics are shown, the first is for longitudinal direction and the second is for the cross direction.
Tolerances	The average values derived from standard tests and are subject to the usual production variations. The indicated average values comply with the UEAtc standard and project prEN 13707. The nominal value tolerances comply with the UEAtc standards. Some slight variations can be noticed as the values are based on the average values obtained from several plants.
Modification(s)	Our company reserves the right to modify its composition as a result of technologic and experiments improvements. This product data sheet supersedes the previous edition, to obtain the up-date technical data sheet, please contact our technical department.
Hazardous classification	It is not classified as dangerous according to the international regulation (ADR, RID, IATA, et RTMDR)
Divers	This product is only a product technical data sheet, regarding each waterproofing design, please, consult the concerned technical agreement and in case of doubt contact our technical department.
Storage	This product is packaged in rolls set up vertically on pallet or wooden box. It must be stored vertically under shelter, away from heat sources.