

PARAFOR SOLO GFX

DESCRIPTION

Very high performance reinforced SBS elastomeric bitumen membrane self-finished by coloured mineral granules for waterproofing works.

It features the PROFIL SYSTEM (SIPLAST patent), which by the selvedge scarifying, highly improves the installation efficiency (homogenous film burn out, total and well-visible compound melting - automatic check for the operator).

This product is for use as :

Membrane mechanically fixed to the roof deck of a single layer roof waterproofing system for inaccessible roof. Guideline with centimetre scale on the selvedge (PROFIL SYSTEM) makes easy the correct positioning of mechanical fixings. It can be also used for miscellaneous works. In either case, this product must be used in accordance with the relevant technical specifications.

COMPOSITION

Main surface	Coloured granules.
Longitudinal overlap surface	Scarified thermo-fusible film with centimetre scale (Profil system).
Blend	Fillerized SBS (Styrene-Butadiene-Styrene) elastomeric bitumen
Reinforcement	Non woven polyester
Underface	Sanded with thermo-fusible film on the selvedge (PROFIL SYSTEM)


DIMENSIONAL CHARACTERISTICS

COLOURS	Slate grey 30 and Schist light 1	Others colours
Nominal thickness on the longitudinal selvedge (mm)	4	4
Nominal thickness on the main surface (for information only) (mm)	4,8	5
Longitudinal selvedge nominal width (mm)	120	120
Roll nominal length and width (m)	7 x 1	7 x 1

PERFORMANCES

KIND OF TEST	Reference Norme	Units	Average values
Tensile strength at max	EN 12 311-1: 1999	N/50mm	850 x 600
Elongation at max	EN 12 311-1: 1999	%	40 x 49
Nail tearing resistance	EN 12 310 - 1	N	300 x 350
Cold temperature flexibility	EN 1109	°C	≤ - 20
Heat flow test	EN 1110	°C	≥ 100
Dimensional stability	EN 1107 - 1	%	≤ - 0,3
Static puncture resistance	EN 12730	kg	20
Impact resistance	EN 12691	mm	1500
FIT classification	Indicated on the relevant Technical Agreement (CSTB)		

ISO 9001 REFERENCE DOCUMENT

. Our company has been awarded the ISO 9001 certificate for all its establishments in France.	
. The Technical Agreement PARAFOR SOLO GFM is the ISO 9001 reference document.	

PACKAGING

COLOURS	Slate grey 30 and Schist light 1	Others colours
Rolls quantity per truck pallet	24	23
Rolls quantity per container pallet	27	25
Rolls quantity per wooden box	25	23
Nominal weight / m ² (kg/m ²)	6.0	6.3
Nominal weight / roll (kg)	41.1	43.4

GENERALITIES ABOUT APPLICATION

Using	The generalities about the product using are set out in the ZSA STANDARD
Application	The generalities about the product application are set out in the ZTA STANDARD
Overlaps	Current building practices concerning overlaps are set out in the ZRA STANDARD
Slopes	Current building practices concerning slopes are set out in the ZPA STANDARD

COMPLEMENTARY INFORMATIONS

Product identification	2 coloured longitudinal side lines on the surface. each one will be at a distance of 100 mm nominal of each side
Values	Where 2 values for given characteristics are shown, the first is for longitudinal direction and the second is for the cross direction.
Tolerances	The average values derived from standard tests and are subject to the usual production variations. The indicated average values comply with the UEAtc standard and project prEN 13707. The nominal value tolerances comply with the UEAtc standards. Some slight variations can be noticed as the values are based on the average values obtained from several plants.
Modification(s)	Our company reserves the right to modify its composition as a result of technologic and experiments improvements. This product data sheet supersedes the previous edition, to obtain the up-date technical data sheet, please contact our technical department.
Hazardous classification	It is not classified as dangerous according to the international regulation (ADR, RID, IATA, et RTMDR)
Complementary information	This product is only a product technical data sheet, regarding each waterproofing design, please, consult the concerned technical agreement and in case of doubt contact our technical department.
Storage	This product is packaged in rolls set up vertically on pallet or wooden box. It must be stored vertically under shelter, away from heat sources.