

Product Technical Information

ITA/ATEXP/453
Rév. 0 – 18/02/10
1/1

FEL'X MULTI

DESCRIPTION

Bitumen sheet used as underlay for discontinuous roofing.

SCOPE OF APPLICATION

Underlay for under roof with underneath ventilation.

Applied upon : Pitched roofs – Discontinuous support – Continuous ventilated wood support.
Applied by : Nailing – Nailing of counter lath.

DESCRIPTION

Surfacing	None woven synthetic
Compound	Elastomeric bitumen
Reinforcement	Nonwoven polyester

DIMENSIONAL CHARACTERISTICS

	Nominal value	Critical value
Length (m)	40	39.8
Width (m)	1.25	1.238
Weight/roll (kg)	25.68	24.40
Weight/m ² (kg)	0.5	0.47

PERFORMANCES

	Norm	Unit	Nominal values	Critical values
Tensile Strength	EN 12311-1	N/5cm	335 x 310	300 x 270
Elongation	EN 12311-1	%	50 x 58	42 x 50
Nail Tearing resistance	EN 12310-1	N	320 x 340	300 x 250
Flexibility at low temperature	EN 1109	°C	-25	
Dimensional stability	EN 1107-1	%	-0.5	
Watertightness	EN 1928		W1	
Water vapour transmissivity	EN 1931	m	25	
Reaction to fire	EN 13501-1		E	